

Investigating Mix Proportions of Self Compacting Concrete Using Taguchi Method

Nishchal Rathore¹, Hitesh Kodwani²

¹Dept of Civil Engineering

²Assistant Professor and Head, Dept of Civil Engineering

^{1,2}Sam College of Engineering and Technology, Bhopal-462021, Madhya Pradesh, India.

Abstract- In order to address the problem of space problem in structural elements having highly congested reinforcement, Self-compacting concrete (SCC) was developed. This research has been done to optimize experimentation process using design of experiments (DoE). Taguchi a standard L (3) orthogonal array (OA) of four factors with three material parameters levels to make a total of 9 number of trail mixes are employed. The factors taken in this study are water powder ratio, cementitious material content, super-plasticizer and steel fibre content. The responses of material factors are examined for maximizing the compressive and tensile strength of self compacting concrete. The outcomes show that the definite proportions of the diverse constituent material assisted to give improved compressive strength and split tensile strength. The steel fibres and fly ash content played an imperative character to increase the compressive and split tensile strength. The function of super plasticizer dose is noted to be relatively high spotted on the fresh concrete characteristics of SCC.

Keywords- Self compacting concrete, Fiber, Super-plasticizers, Admixture.

I. INTRODUCTION

In Japan and Europe, Self-compacting concrete was initially developed. It is a type of concrete that is capable to flow and fill every division of the corner of the formwork (In shuttering), even when the dense reinforcement is present, purely by means of its own weight and exclusive of any vibration or other type of voids removal process.

In 1986 the development of SCC has made a major impact on the construction industry by prevail over some of the difficulties associated to freshly readied concrete. Several difficulties has been reported when it is in fresh form like skill of workers, type and configuration of a structural section, density of reinforcement, ability to pump, resistance to segregate and mostly compaction. Self compacting concrete is rich in fines content and found to be more lasting. Numerous researches have been listed on the global growth of SCC and its micro-social system and strength aspects. Instead of various

researches and construction systems conducted widespread, the Bureau of Indian Standards (BIS) has not fixed out a standard mix method to get proper mix design trials and self-compact capacity testing methods. The behavior of Self Compacting Concrete is same as that of conventional concrete comprises of binder, fine aggregate, coarse aggregates, water, fines and admixtures. In order to get the rheological properties of SCC. SCC should have more fines content, super plasticizers with viscosity modifying agents (VMA) to some extent.

II. OBJECTIVES OF PRESENT STUDY

Following are the objectives of the thesis

1. To develop a systematic methodology for determining the optimum proportions of different parameters which gives high flow ability, passing ability and highest value of compressive strength and tensile strength.
2. To analyze the influence of different factors at different levels by using Taguchi method (DoE).

III. LITERATURE REVIEW

The relevant literature pertaining to the present research carried out in India and abroad has been reviewed and presented as under:-

Emara et al. (2018) did the experimental study to know the effect and optimization of self-compacting rubberized concrete by using Taguchi method. Design of experiment was carried out through orthogonal array to accommodate four factors with four levels. These factors are the percentage of coarse rubber, fine rubber, viscrete and fly ash in the concrete mix. To study the performance features of self-compacting rubberized concrete, the S/N ratio and the analysis of variance are utilized. The result specifies that there is a drop in the strength with increasing rubber content but apparently increase in impact resistance has been observed.

Khalil et. al. (2015) worked on the mechanical properties and workability of Self compacting rubberized concrete in order to diminish the negative effect of rubber aggregate on the characteristics.

The effects on the mechanical properties of FRC are analyzed through the volume fraction and length of basalt fiber has been noticed by **Jiang et al (2014)**. The upshot specifies that adding basalt fiber appreciably enhances the flexural strength, tensile strength and toughness index. Whereas, there is no any major change in compressive strength observed. Besides this, the length of basalt fiber presents the effects on the mechanical properties.

An experimental study has been performed by **Bhalchandra et.al. (2012)** to notice the change in compressive strength and flexural strength over normal SCC by using steel fibre content and found the 25.75% and 19.47% increment in compressive strength and flexural strength respectively over normal SCC.

Abdulhadi et al. (2012) used polypropylene fiber in M30 grade concrete. Compressive, split tensile strength and a relation between them has been obtained. The range of polypropylene fiber is kept between 0% to 1.2% volume fractions by weight of cement.

IV. DESIGN OF EXPERIMENT

Design of Experiment (DoE) is a organized approach to get better the quality of given material parameters. This investigational work was performed to examine the effect of steel fibres at diverse dosage of cementing material and superplasticizer. The design of experiments (DoE) was employed by Taguchi to optimize experimentation process and these simultaneously improved techniques are called “Taguchi method” which decreases the number of experiments. By using the typical proportion materials shown in Table 1, 9 mixes of self-compacting concrete (SCC) are evaluated and detailed in Table 3.

Table 1- Mix parameters and their levels

Variable	Water Cement Ratio		Fly Ash		Steel Fibres		Superplasticizer	
	Code	Absolute	Code	Absolute	Code	Absolute	Code	Absolute
1	P1	0.4	Q1	0	R1	50	S1	0.8
2	P2	0.38	Q2	20	R2	30	S2	1.2
3	P3	0.36	Q3	40	R3	15	S3	1.6

In this study, a standard L₉ (3⁴) orthogonal array (OA) of four parameters with three material factors levels to

vary a total of 9 trail mixes. L₉ orthogonal array are used Table 2.

Table 2- Design matrix of L₉ (3⁴) orthogonal array with parameters and their coding

Variable	Variable 1		Variable 2		Variable 3		Variable 4	
	Water Cement Ratio (%)		Fly Ash (%)		Steel Fibres (mm)		Superplasticizer (%)	
	Code	Absolute	Code	Absolute	Code	Absolute	Code	Absolute
1	P1	0.4	Q1	0	R1	50	S1	0.8
2	P1	0.4	Q2	20	R2	30	S2	1.2
3	P1	0.4	Q3	40	R3	15	S3	1.6
4	P2	0.38	Q1	0	R2	30	S3	1.6
5	P2	0.38	Q2	20	R3	15	S1	0.8
6	P2	0.38	Q3	40	R1	50	S2	1.2
7	P3	0.36	Q1	0	R3	15	S2	1.2
8	P3	0.36	Q2	20	R1	50	S3	1.6
9	P3	0.36	Q3	40	R2	30	S1	0.8

By using the typical proportion materials shown in Table 3.4, 9 mixes of self-compacting concrete (SCC) are evaluated and detailed in Table 3.

Table 3 Details of Mix Proportion

Experiment No.	Water (kg/m ³)	Cement (kg/m ³)	Fly ash (kg/m ³)	F.A (kg/m ³)	C.A (kg/m ³)	HRWR (kg/m ³)	Steel fibres (kg/m ³)
1	215	510	0	1008	781	4.08	4.4
2	215	408	102	1008	781	6.12	4.4
3	215	306	204	1008	781	8.16	4.4
4	194	510	0	1008	781	8.16	4.4
5	194	408	102	1008	781	4.08	4.4
6	194	306	204	1008	781	6.12	4.4
7	174	510	0	1008	781	6.12	4.4
8	174	408	102	1008	781	8.16	4.4
9	174	306	204	1008	781	4.08	4.4

The purpose is to pick the best mixture of control parameters so that the product or process is most robust. The obtained results are given in table below:

Table 4- Experimental Results

Experiment No.	Fresh concrete test		Hardened concrete test			
	Slump flow(mm)	L-box (h2/h1)	Compressive strength (MPa)		Split tensile strength (MPa)	
			7th day	28th day	7th day	28th day
Mix no.1	692	0.89	28	38	2.05	2.57
Mix no.2	710	0.94	26	42	2.02	2.92
Mix no.3	730	0.96	25	40	2	2.85
Mix no.4	700	0.94	34	46	2.22	2.88
Mix no.5	692	0.89	28	44	2.16	3.02
Mix no.6	690	0.86	23	39	1.96	2.48
Mix no.7	668	0.84	32	42	2.32	2.98
Mix no.8	685	0.86	26	40	2.14	2.8
Mix no.9	680	0.86	26	39	2.12	2.82




Fig.1. - 7 days and 28 days Compressive Strength




Fig.2. - 7 days and 28 days Split Tensile Strength

V. DISCUSSIONS AND CONCLUSIONS

From the results of present research following conclusions were drawn-

1. The best proportion for slump flow and L-box result are found for water powder ratio at P1 (0.42%), fly ash % at Q3 (40%), steel fibre type at R3 (15mm) and super plasticizer content at S3 (1.6%). In addition to this, the slump flow value of 9 trial mixes found in the range of

550mm to 800mm. From L-Box test, satisfactory results have been shown for passing ability ratio in all trials.

2. The optimum ratio for 7th day compressive strength are obtained at water powder ratio at P2 (0.38%), fly ash % at Q1 (0%), steel fibre type at R2 (30mm) and super plasticizer content at S3 (1.6%). Whereas best results for 28th days compressive strength are noted at water powder ratio at P2 (0.38%), fly ash % at Q1 (0%), steel fibre type at R2 (30mm) and super plasticizer content at S3 (1.6%).
3. In case of 7th Days split tensile strength, the optimum proportion is obtained at water powder ratio at P3 (0.34%), fly ash % at Q1 (0%), steel fibre type at R3 (15mm) and super plasticizer content at S2(1.2%). Though, The most favourable proportion for 28th day split tensile strength are found at water powder ratio at P2 (0.38%), fly ash % at Q2 (20%), steel fibre type at R3 (15mm) and super plasticizer content at S1 (0.8%).
4. It has been observed that when there is enhancement in fly ash % of the mix, the flow ability and passing ability increases. However, the best possible dosage of fly ash from the fresh test result is found at 40% replacement of cement material and best hardened properties of concrete are found at 20% fly ash substitution from cement.
5. It has also been noted that super plasticizer doesn't take much role in a strengthening of concrete but it executes critical role in a fresh behavior of SCC. The optimum dosage of super plasticizer observed from the results is 1.6% by weight of cement which gives enhanced self-compacting features to the concrete.
6. According to these experimental results, all the 9 mixes are able to establish a higher strength concrete exclusive of vibration, with fulfills all the workability necessities of SCC as per EFNARC.
7. A linear decrement of workability characteristics (passing ability, filling ability and segregation resistance) of the SCC mixes has been observed with reducing water-cement ratio.

REFERENCES

- [1] M. A. Emara, F. M. Eid, A. A. Nasser, M. A. Safaan "Prediction of Self-Compacting Rubberized Concrete Mechanical and Fresh Properties using Taguchi Method", Journal of Civil & Environmental Engineering Vol. 8, Issue 2, 2018.
- [2] J. Chaohua Jiang, K. Fan, F. Wu, D. Chen, "Experimental study on the mechanical properties and microstructure of chopped basalt fiber reinforced concrete", Materials and Design 58 (2014) 187–193.
- [3] E. Khalil, M. Abd-Elmohsen, M.A. Anwar (2015) Impact resistance of rubberized self-compacting concrete. Water Sci 29: 45-53.

- [4] S.A. Bhalchandra and A.B. Pawase, “Performance of Steel Fibre Reinforced Self Compacting Concrete”, International Journal of Computational Engineering Research (IJCER) Vol. 2 Issue.
- [5] M. Abdulhadi, A comparative Study of Basalt and Polypropylene Fibers Reinforced Concrete on Compressive and Tensile Behavior”, International Journal of Engineering Trends and Technology (IJETT) – Volume 9 Issue 6- March 2012.