A Review on Thermal Energy Storage Systems With Phase Change Materials

J. Ramesh¹, B. Melina Queen², K. Sagar Kumar³, Dr. E. Venkata Subbareddy⁴

^{1,2,3} Assistant Professor, Dept of Mechanical Engineering ⁴Professor, Dept of Mechanical Engineering ^{1,2,3} Dr. KVSRIT, Kurnool, AP, India ⁴Sanskrithi School of Engineering, Puttaparthi, AP, India

Abstract- In the current situation of an enormous energy demand, dependency on fossil fuels only, actually creates crisis in future particularly for developing country. Although renewable resources of energy like solar power is being utilised on a broad scale nowadays however the matter comes in law and economy i.e. social and acceptability. Main reasons of this type of difficulties are density of radiation on earth's surface and if it's available then unsteady in nature with time of the day and the day of the year. To remove these types of difficulties solar power storage unit should be introduced in solar thermal power application. In this paper, literatures on thermal energy storage unit with phase change material has been strictly studied to pick out the most effective appropriate PCMs and materials for the design of test bench of the thermal energy storage unit.

Keywords- Thermal Storage, Phase change materials, sensible latent heat storage, solar energy.

I. INTRODUCTION

In the present scenario when the demand is more than resources available, it's our necessity to develop an energy storage device to store energy at the time of availability and supply it whenever demand is more than available. Although Sensible heat storage is the most common method of thermal energy storage, but the recent research on advance material and system shows that density of stored energy is greater for latent heat storage than that of sensible heat storage. Phase change material is generally used in latent heat storage system and this type of system has been widely used for heat pumps, solar engineering, and spacecraft thermal control applications. Tremendous increase in the price of fossil fuel and continuous upgrading in the level of greenhouse gas emissions are the main driving forces behind the effective utilization non conventional energy resources. The storage of energy in suitable forms, conveniently converted into the required form, is a present day challenge to the technologists. Solar energy storage unit has the following characteristics

- (a) To conserve energy
- (b) To improve the performance and reliability of energy systems and
- (c) To reduce the mismatch between supply and demand. Scientists in many parts of the world are in search of new and renewable energy resources and stated that direct solar radiation is a prospective renewable source of energy and the solar energy storage unit is the new source of energy. In other words solar energy storage unit can be called as the sub renewable sources of energy. There are various kinds of phase change materials but paraffin has been widely used for latent heat thermal energy storage system because of their large latent heat and proper thermal characteristics such as no super cooling, low vapour pressure, good thermal and chemical stability and self nucleating behavior..

II. ENERGY STORAGE METHODS

There are various forms of energies and their storage methods or mechanisms have been described below. Atul Sharma et al. describes in their review paper on, thermal energy storage with phase change materials and applications, about different type of energy storage methods and their mechanisms. In this paper main emphasis is given to the latent heat storage method to store solar thermal energy. J. Ramesh at al. fabricated a double slope type solar still with reflecting mirrors to store and increase the intensity of solar energy on solar still[30].

2.1. Mechanical energy storage

Mechanical energy storage systems include the storage due to gravitation as for example hydropower storage, storage due to pressure difference, compressed air energy storage and storage due to inertia, flywheels. Hydropower storage and compressed air energy storage can be used for large scale utility of energy while flywheels are more suitable for intermediate storage. Storage is carried out when off-peak power is available

Page | 610 www.ijsart.com

and the storage is discharged when power is needed because of insufficient supply from the base-load plant.

2.2. Electrical energy storage

Electrical energy is stored through batteries. When the battery is connected to the direct electric current then ionic reactions happens where the positive and negative ions are separated and hence chemical potentials are formed. At the time when the main supply disappears, this chemical energy is converted into electrical energy. The most common type of storage batteries is the lead acid and Ni–Cd. Potential applications of batteries are utilization of off-peak power, load leveling, and storage of electrical energy generated by wind turbine or photovoltaic plants.

2.3. Thermal energy storage

Thermal energy can be stored as a change in internal energy of a material as sensible heat, latent heat or thermo chemical or combination of these. Sensible heat storage is due to temperature change of material while latent heat storage is due to the phase transformation either it is solid-liquid, liquid-gas or solid-solid. Different types of thermal energy storage of solar energy are discussed below. J. Ramesh at al. fabricated a flat plate and parabolic trough solar collectors for concentrating the intensity of solar energy on for hot water generation [31, 32]

2.3.1. Sensible heat storage

In sensible heat storage (SHS), thermal energy is stored by raising the temperature of a solid or liquid. SHS system utilizes the heat capacity and the change in temperature of the material during the process of charging and discharging. The amount of heat stored depends on the specific heat of the medium, the temperature change and the amount of storage material.

Water appears to be the best SHS liquid available because it is inexpensive and has a high specific heat. However above 100oC, oils, molten salts and liquid metals, etc. are used. For air heating applications rock bed type storage materials are used.

2.3.2. Latent heat storage

In latent heat storage system charging and discharging phenomenon occur when the storage material undergoes phase change either from solid to liquid, liquid to gaseous or solid to solid. The storage capacity of latent

heat storage system with a PCM medium is evaluated using various relations.

2.4. Thermo chemical energy storage

Sharma et al said that charging and discharging phenomenon takes place during the breaking and reforming of molecular bonds in a complete reversible chemical reaction. In this case heat stored depends upon the amount of storage material, the endothermic heat of reaction, and the extent of conversion

Above discussed thermal energy storage technique, latent heat storage technique is one of the best suitable technique because of its high energy storage density and its characteristics to store heat at constant temperature called phase transition temperature of phase change material. Phase change can be in the following form: solid-solid, solid-liquid, solid-gas, and liquid-gas and vice versa

III. CLASSIFICATION OF PCMS

The materials which are to used for thermal energy storage unit must have a high value of latent heat and thermal conductivity. They should have melting temperature lying in the practical range of operation, melt congruently with minimum sub cooling and be chemically stable. It should be low in cost, nontoxic and noncorrosive. Materials that have been studied during the last 40 years are hydrated salts, paraffin waxes, fatty acids and eutectics of organic and nonorganic compounds. Phase change materials should first be selected on the basis of their melting temperature and their applications. For air conditioning purposes, materials of melting temperature below 15oC is to be selected, while materials that melts above 90oC are used for absorption refrigeration system. All other materials that melt between these two temperatures can be applied in solar heating and for heat load leveling applications. These materials represent the class of materials that has been studied most

3.1 Organic phase change materials

Organic PCMs are further described as paraffins and non paraffins. The main interest with organic materials is that they involve long term cyclic chemical and thermal stability without phase segregation and consequent crystallize with little or even no supercooling. Finally, they are non corrosive which is an important feature as listed previously. Subgroups of organic materials include paraffin and non-paraffin organics. Paraffin consists of a mixture of n-alkanes CH3-(CH2)-CH3 into which the crystallization of the (CH3) - chain is responsible for a large amount

Page | 611 www.ijsart.com

of energy absorption. The latent heat of fusion of paraffin varies from nearly 170 kJ/kg to 270 kJ/kg between 5oC to 80oC which makes them suitable for building and solar applications. Non-paraffin organic materials are the most common of the PCMs and they involved varying properties. Buddhi and Swaney have conducted an extensive survey of esters, fatty-acids, alcohols and glycols suitable for energy storage. These materials generally have a high heat of fusion but low thermal conductivity, inflammability, toxicity, and instability at high temperatures. Although fatty acids are somewhat better than other non paraffin organics, they are even more expensive than paraffins. The development of a latent heat thermal energy storage system involves the understanding subjects: phase change materials, three essential containers materials and heat exchangers.

3.2. Inorganic phase change materials

Inorganic compounds include salts hydrate, salts, metals, and alloys. The first were investigated because of their low cost which is determinant in most projects. Moreover, inorganic PCMs permit high density storage because they have high volumetric latent heat storage capacity and their conductivity may be twice as high as that of organic materials. The authors used salt hydrates but experienced supercooling, phase segregation, and a lack of thermal stability. Moreover, it is reported that some are corrosive. Supercooling and phase segregation could be prevented in some cases but then the economics may suffer. Metallic PCMs are low melting point metals such as Galium and metal eutectics. These have not yet been investigated thoroughly because of their weight. However, when volume is a major issue, they could be considered as they have high latent heat of fusion and very high conductivities compared to other PCMs.

3.3 Eutectics

A eutectic is a minimum-melting composition of two or more components, each of which melts and freezes congruently forming a mixture of the component crystals during solidification. A large number of eutectics of inorganic and organic compounds have been reported. Eutectics are generally better than straight inorganic PCMs with respect to segregation

IV. COMPOSITE PCMS

Vasishta D. Bhatt et al. presents nine most suitable PCMs for thermal energy storage device. They studied rigorously about sixty PCMs and select most suitable

PCMs based on the properties like thermal conductivity, heat of fusion, density and melting point. For the enhancement of storage capacity and different properties of phase change materials for the suitability of thermal energy storage device. Moussa Aadmi et al. present the composite PCMs, epoxy resin paraffin wax with melting point 27oC as a new energy storage system. Ahmet Sari et al. determines the thermal properties of blends of Polyvinyl alcohol(PVA)-stearic acid(SA) and chloride(PVC)-stearic acid(SA) as form stable phase change material for thermal energy storage. In the blend,SA has a function of storing latent heat of fusion during its solid-liquid phase change where as the polymer(PVC or PVA) acts as a supporting material to prevent melted SA leakage because of its structural strength. A variety of polymer matrices are available with a large range of chemical and mechanical properties.

V. DEVELOPMENT OF LHSS

Latent heat storage material stores thermal energy while undergoing a phase transformation. Developments of these storage systems include selection of material of desirable properties, material of containment and compatibility between these two. Initially latent heat storage material behaves like a conventional storage material but once the phase transition temperature reached, it acts as a latent heat storage material. Latent heat thermal energy storage system stores 5-14 times more heat than sensible heat thermal energy storage material as mentioned above. After the selection of latent heat storage material, there must be a concept to develop heat exchanger which takes the stored heat away from phase change material and send it to the helical coil solar cavity receiver present at the focus of parabolic trough concentrator under consideration.

VI. CONCLUSION

Thermal energy storage unit is integrated with solar thermal power station so as to supply continuous power even at late evenings or in the situation when the cloud covering is occur in the sky. In this paper, numerous kinds of storage unit are represented however main emphasis is given to thermal energy storage unit with the assistance of phase change material.

Different kinds of PCMs and their properties have been described in this paper but a special and the most recent type of PCMs called composite PCMs has also been described. Composite PCMs are the materials that have the improved properties like thermal conductivity, heat of fusion, density and melting point in comparison to single PCM like

Page | 612 www.ijsart.com

paraffin wax etc. So, if serious attention is going to be given to composite phase transition materials then a much better and most effective thermal energy storage unit will be designed. Latent heat thermal energy storage system stores 5-14 times more heat than smart heat thermal energy storage material. By considering as a whole it has a tendency to return to the conclusion that latent thermal energy storage is most economical and their strong design might lead to store the maximum amount of energy to provide continuously to the spiral coil solar cavity receiver system of parabolic trough concentrator. There are massive numbers of phase change materials however few of them are used in accordance with the applications. For air conditioning purposes, materials of melting temperature below 15oC is to be selected, while materials that melts above 90oC are used for absorption refrigeration system. All alternative materials that melt between these two temperatures will be applied in solar heating and for thermal load leveling applications. Selection of phase transition material and its compatibility with the containment wherever PCM encapsulated is the main issue to design most effective thermal energy storage unit

REFERENCES

- [1] Izquierdo-Barrientos MA, Sobrino C, Almendros-Ibáñez JA, Thermal energy storage in a fluidized bed of PCM, Chemical Engineering Journal 230 (2013) 573–583.
- [2] Zalba B, Marín JM, Cabeza LF, Mehling H, Review on thermal energy storage with phase change: materials, heat transfer analysis and applications, Appl.Therm. Eng. 23 (2003) 251–283.
- [3] Cabeza LF, Castell A, Barreneche C, De Gracia A, Fernández AI, Materialsused as PCM in thermal energy storage in buildings: a review, Renew. Sust.Energ. Rev. 15 (2011) 1675–1695.
- [4] Regin AF, Solanki SC, Saini JS, Heat transfer characteristics of thermal energy storage system using PCM capsules: a review, Renew. Sust. Energ. Rev.12 (2008) 2438–2458.
- [5] Atul Sharma, Tyagi VV, Chen CR, Buddhi D, Review on thermal energy storage with phase change materials and applications, Renewableand Sustainable Energy Reviews 13 (2009) 318–345.
- [6] Garg HP, Mullick SC, Bhargava AK. Solar thermal energy storage. D.Reidel Publishing Co; 1985.
- [7] Project Report. Energy conservation through thermal energy storage. An AICTE project.
- [8] Abhat A, Low temperature latent thermal energy storage system:heat storage materials, Sol. Energy 30 (1983) 313332.

- [9] Sharma SD, Sagara K, Latent heat storage materials and systems: a review, Int. J. Green Energy 2 (2005) 156.
- [10] Zalba B., Marin JM, Cabeza L.F, Mehling H, Review on thermal energy storage with phase change: materials, heat transfer analysis and applications, Appl. Therm. Eng. 23 (2003) 251283.
- [11] Himran S, Suwono A, Mansoori GA, Characterization of alkanes and paraffin waxes for application as phase change energy storage medium, Energy Sour. 16 (1994) 117,128.
- [12] Liu X, Liu H, Wang S, Zhang L, Cheng H, Preparation and thermal properties of form stable paraffin phase change material encapsulation, Energy Conver. Manag. 47 (2006) 25152522.
- [13] Lane GA. Solar heat storage—latent heat materials, vol. I. Boca Raton, FL: CRC Press, Inc.; 1983.
- [14] Daniel. R. Rousse, Nizar Ben Salah, and Stéphane Lassue, An Overview of Phase Change Materials and their Implication on Power Demand, National Science and Engineering Research Council of Canada.
- [15] Farid MM, Khudhair AM, Razack SAK, and Al-Hallaj S, A review on phase change energy storage: materials and applications, Energy Conversion and Management, vol. 45(9-10), pp.1597-1615, June 2004.
- [16] Zhang Y, Zhou G, Lin K, Zhang Q, and H. Di, Application of latent heat thermal energy storage in buildings: State-of-the-art and outlook, Building and Environment, vol. 42(6), pp2197-2209, June 2007.
- [17] Mohammed M. Farid , Amar M. Khudhair , Siddique Ali K. Razack ,Said Al-Hallaj, A review on phase change energy storage: materials and applications, Energy Conversion and Management 45 (2004) 1597– 1615.
- [18] Senthilkumar R,Sithivinayagam N, Shankar, Experimental Investigation of Solar Water Heater Using Phase Change Material, International Journal of Research in Advent Technology, Vol.2, No.7, July 2014 E-ISSN: 2321-9637.
- [19] Buddhi D, Sawhney RL, Proceedings on thermal energy storage and energy conversion, 1994.
- [20] Abhat A,Low temperature latent heat thermal energy storage: heat storage materials. Solar Energy , vol. 30. pp.313-332, 1983.
- [21] Younsi Z, Lassue S, Zalewski L, Rousse DR, and Joulin A, A novel technique for the experimental thermophysical characterization of phase change materials, (paper submitted to Energy Conversion Management).
- [22] Herrick S. A rolling cylinder latent heat storage device for solar heating/cooling. ASHRAE Trans, vol. 85, pp. 512-515, 1979.

Page | 613 www.ijsart.com

- [23] George A, Phase change thermal storage materials. In Hand book of thermal design. Guyer C, Ed., McGraw Hill Book Co., 1989.
- [24] HasnainSM, Review on sustainable thermal energy storage technologies, Part 1: heat storage materials and techniques. Energy ConversionManagement, vol. 39, pp. 1127-1138, 1998.
- [25] Lane GA, Solar heat storage: latent heat materials, vol. 1. USA: CRC Press Inc.; 1983.
- [26] Vasishta D. Bhatt, Kuldip Gohil, Arunabh Mishra, Thermal Energy Storage Capacity of some Phase changing Materials and Ionic Liquids, International Journal of ChemTech Research, CODEN (USA): IJCRGG ISSN: 0974-4290, Vol.2, No.3, pp 1771-1779, July-Sept 2010.
- [27] Moussa Aadmi, Mustapha Karkri, Mimoun El Hammouti, Heat transfer characteristics of thermal energy storage of a composite phase change materials: Numerical and experimental investigations, Energy 72 (2014) 381-392.
- [28] Ahmet Sari, Murat Akay, Mustafa Soylak and Adem Onal, Polymer stearic acid blends as form-stable phase change material for thermal energy storage, Journal of Scientific & Industrial Research, Vol. 64, December 2005, pp. 991-996.
- [29] Peng S, Fuchs A, Wirtz RA. Polymeric Phase Change Composites for Thermal Energy Storage Sci 2004;93:1240–51.
- [30] J. Ramesh, Dr. EV Subbareddy, Dr. B. Durga Prasad, "Water purification using a fabricated double slope type solar still with external reflecting mirrors", International Journal of Innovative Research in Science, Engineering and Technology, vol. 6, issue 5, (2017), pp. 7484-7490.
- [31] J.Ramesh, J.Kanna Kumar, Dr.E.V.Subbareddy, "Design, Fabrication and Performance Analysis of a Parabollic trough Solar Collector Water Heater", International Journal of Innovative Research in Science, Engineering and Technology, Vol. 4, Issue. 7, (2015), pp. 6038-43
- [32] J.Ramesh, J.Kanna Kumar, Dr.E.V.Subbareddy, "Fabrication and Performance Evaluation of a Flat Plate Solar Collector Water Heater", International Journal of Innovative Research in Science, Engineering and Technology, Vol. 6, Issue. 4, April 2017, pp. 5293-5299

Page | 614 www.ijsart.com