

# Water Absorbing Pavements By Using Porous Concrete

Rohit Dhansing Kadam<sup>1</sup>, Shantanu Baban Bhumkar<sup>2</sup>, Ajit Balasaheb Korade<sup>3</sup>,  
Swapnil Sairam Pawar<sup>4</sup>, Niranjana Jaganath Bhokare<sup>5</sup>

<sup>1,2,3,4,5</sup> Dept of Civil Engineering

<sup>1,2,3,4,5</sup> Zeal Polytechnic SR NO. 39, Narhe, Pune 411041, Maharashtra India

**Abstract-** Water Absorbing pavement is a new technique in Pavement construction. Through this technique we can find a solution for the low ground water level, effective management of storm water runoff, Agricultural problems, etc. Pervious concrete can be introduced in low traffic volume areas, walk ways, sub base for concrete pavements, inter locking material etc. Pervious concrete as a paving material have the ability to allow water to flow through itself to recharge ground water level and minimize surface storm water runoff. This property of porous concrete reviews its applications and engineering properties, including environmental benefits, strength and durability. By replacing a part of cement with flash, then it results the safe disposal of waste material. Hence it acts as an eco- friendly paving material.

**Keywords-** Pervious Concrete, Storm Water, Ground water Recharging, Light Weight, Waste Material Management, Strength, Durability...

## I. INTRODUCTION

Porous pavement is a storm water drainage system that allows rain water and runoff to move through the pavements surface to storage layer below, with the eventually seeping into the underlying soil. Permeable pavement is beneficial to the environment because it can reduce storm water volume, treat the storm water quality, and replenish the ground water supply and lower air temperatures on hot days. Due to increased void ratio, water conveyed through the surface and allowed to infiltrate and evaporate, whereas conventional surfaces will not do so. A porous pavement surface therefore becomes an active participant in hydrological cycle: rain fall and snow melt are conveyed back through soil into ground water. And also this pavement technology creates more efficient land use by eliminating the need for retention ponds, swales, and other storm water management devices. In doing so, pervious concrete has concrete, carefully controlled amounts of water and cementitious materials are used to create a paste that forms a thick coating around aggregate particles. A pervious concrete mixture contains little or no sand, creating a substantial void content. And that's why it is also known as No fines Concrete. Using sufficient paste to coat and

bind the aggregate particles together creates a system of highly permeable, interconnected voids that drain quickly. For porous concrete, water permeability is the main specification requirement instead of its strength and continuity of the open pores is the main concern in the production of porous concrete. The high water permeability of porous concrete makes it to be considered as an environmentally friendly concrete. When the component materials of porous concrete, environmentally unfriendly Portland cement is partially replaced by supplementary cementitious materials, such as fly ash, ground granulated blast furnace slag and coarse aggregates by recycled concrete aggregate, then the porous concrete could be considered as environmentally concrete for sustainable construction.

## What is a no-fine concrete

Pervious concrete is a structural concrete pavement with a large volume (15 to 35percent) of interconnected voids. Like conventional concrete, its made from a mixture of cement, coarse aggregates, and water. However, it contains little or no sand, which results in a porous open- cell structure that water passes through readily.

## Environmental Benefits

- Reduce the surface runoff of the storm water
- Pervious concrete pavement reduces or eliminates runoff and permits natural treatment of runoff water
- By collecting rainfall and allowing it to infiltrate, groundwater, aquifer recharge, water table level is increased
- Pervious concrete is a light weight pavement material
- Effective utilization of waste material such as flyash makes this technique more eco- friendly
- Pervious concrete pavement is ideal for protecting trees in a paved environment.
- Although high-traffic pavements are not a typical use for pervious concrete, concrete surfaces also can improve safety during rainstorms by eliminating ponding

## II. PREVIOUS RESEARCH

**M. Admute, A. V. Gandhi, S. S. Adsul, A. A. Agarkar,(April2017),"Permeable Pavements: New Technique For Construction Of Road Pavements in India"**

In this paper they summarize literature on permeable pavements, highlight current trends in research and industry, and to recommend future areas of research and development. Permeable pavements have a base and sub base that allow the movement of storm water through the surface and hence reduce runoff, this effectively traps suspended solids and filters pollutants from the water. Permeable pavement control storm water at the source, reduce runoff, reduce cost and improve water quality by filtering pollutants in the substrata layers and increase subsurface water level. And also deals with make use of industrial waste fly ash in construction, by partial replacement of cement.

**Jeet Yadu(2016)"Permeable Pavement & its Application A Case Study"**

He summarized literature on study of construction and application of such a pavement which is permeable in nature. The problem related to scarcity of water arriving due to increasing area of paved surfaces has been considered. A detailed study has been made in Raipur city and views are focused in the direction of water conservation through enhancing the ground water recharge. It also deals with the advantages and disadvantages of this pavement system. Permeable pavement are not so complex and are easy to install ,they have many advantages like ground water recharging, storm water management and applications of permeable pavement is depends on various aspects such as climate ,area of application, traffic volume and load.

**Stephen.A.Arhin,Rezene,WasiKhan,(December2014), "Optimal Mix Design for Previous Concrete for Urban Area"**

In this paper they developed and tested five design mixes of pervious concrete to identify the appropriate mix which provided the maximum compressive strength with acceptable permeability rate and flexural strength for the district of Colombia. They conducted five designs mixes using three different types of compaction method such as self-consolidating, half ridding, and standard proctor hammer. They concluded that, the standard Proctor Hammer Compaction method appears to be Optimum procedure for preparing the pervious concrete and having compressive strength 3500psi and permeability in between the range of 57.8. And 299.5 in/hr.

## III. MATERIALS

### Cement

53 Grade OPC provides high strength and durability to structure because of its optimum particle size distribution and superior crystalized structure. Being a high strength cement, it provides numerous advantages wherever concrete for special high strength application is required, such as in the construction of skyscrapers, bridges, flyovers, chimneys, runways, concrete roads and other heavy load bearing structures.

### Coarse Aggregate

Coarse aggregate was used as a primary ingredient in making the permeable concrete. Larger aggregates provide a rougher surface. Recent uses for pervious concrete have focused on parking lots, low-traffic pavements, and pedestrian walkways. For these applications, the smallest sized aggregate feasible is used for aesthetic reasons. Coarse Aggregates are those that are retained on the sieve of mesh size 4.75 mm. Their upper size is generally around 7.5 mm. Gravels from river bed are the best coarse aggregates in the making of Common Concrete.

### Water

Water to cementitious materials ratios between 0.34 and 0.40 are used routinely with proper inclusion of chemical admixtures, and those as high as 0.45 and 0.52 have been used successfully. The relation between strength and water to cementitious materials ratio is not clear for pervious concrete because unlike conventional concrete, the total paste content is less than the voids content between the aggregates.

### Admixture

Chemical admixtures are used in pervious concrete to obtain special properties, as in conventional concrete. Because of the rapid setting time associated with pervious concrete, retarders or hydration-stabilizing admixtures are used commonly. Here we used two different admixtures such as fly ash and conplast sp 500. Fly ash The burning of harder, older anthracite and bituminous coal typically produces Class F fly ash. This fly ash is pozzolonic in nature, and contains less than 20% lime (CaO). It is a fine powder which is byproduct from burning pulverized coal in electric generation power plants and It is a pozzolan, a substance containing aluminous and silicious materials that forms cement in the presence of water. Class F fly ash, with particles covered in a kind of melted

glass, greatly reduces the risk of expansion due to sulphate attack as may occur in fertilized soils or near coastal areas.

Conplast sp 500 Conplast SP500 complies with IS: 9103:1999 and BS: 5075 Part 3 .Conplast SP500 conforms to ASTM-C494Type 'G. It is the high performance water reducing and super plasticizing admixture. Conplast SP500 is based on Sulphonated Naphthalene Polymers and is supplied as a brown liquid instantly dispersible in water. Conplast SP500 has been specially formulated to give high water reductions upto 25% without loss of workability or to produce high quality concrete. The main advantages of this admixture are improved workability, increased strength, improved quality, higher cohesion and chloride free.

#### IV. METHODOLOGY

**Mixing:-** Mix the cement and coarse aggregate on a water tight none-absorbent platform until the mixture is thoroughly blended and is of uniform colour Add the conplast SP430 in water and stir properly and pour into cement and coarse aggregate mixture. Mix it until the concrete appears to be homogeneous and of the desired consistency.

**Sampling :-**Clean the moulds and apply grease. Fill the concrete in the moulds in 3 equal layers Compact each layer with not less than 35 strokes per layer using a tamping rod (steel bar 16mm diameter and 60cm long, bullet pointed at lower end). Level the top surface and smoothen it with a trowel compaction of pervious concrete with tamping rod.

**Curing and Specimens:-**The test specimens are stored in moist air for 24 hours and after this period the specimens are marked and removed from the moulds and kept submerged in clear fresh water until taken out prior to test.

**Infiltration test:-**Infiltration test was carried out with reference of the test procedure given in ASTM C1701. Infiltration test was used for finding the water passing ability of pervious concrete panel which was casted and placed in field. Infiltration test has been carried out manually. The test consists of four main components: Installing the infiltration ring, prewetting the concrete, testing the concrete and calculating the results. For infiltration rate test of pervious concrete panel of 150mm x 150mm x 150mm were casted. The ring is then placed on the cleaned surface and secured in place with plumber's putty. Then water is poured onto the surface and measuring the time for the free water to disperse. With the help of measured volume of water, time required for draining out all the water and cross sectional area of cube Infiltration rate of Pervious Concrete is found out. In this experiment study infiltration rate carried out on panel with mud operation and without it.

**Compression testing machine :-**Generally the compressive strength of the pervious concrete is less the conventional concrete to justify the various compressive strength of cube with different fine fractions this test is conducted. Compressive strength is the resistance of a material to breaking under compression.

- Remove the specimen from water after 7 days curing time and wipe out excess water from the surface
- Clean the bearing surface of the testing machine.
- Place the specimen in the machine in such a manner that the load shall be applied to the opposite sides of the cube cast.
- Align the specimen centrally on the base plate of the machine.
- Rotate the movable portion gently by hand so that it touches the top surface of the specimen.
- Apply the load gradually without shock and continuously at the rate of 140 kg/cm<sup>2</sup>/minute till the specimen fails.
- Record the maximum load and note any unusual features in the type of failure.

#### V. ADVANTAGES & DISADVANTAGES

##### Advantages

1. Effective surface Runoff Management Permeable paving surface allows water to percolate through itself. They are effective in managing runoff from paved surfaces, thus providing local flood control.
2. Control over Pollutants Permeable paving surfaces keep the pollutants in place in the soil or other material underlying the roadway, and allow water seepage to groundwater recharge while preventing the stream erosion problems
3. Ground Water Recharge Permeable pavement contributes a lot in to ground water recharge.
4. Reduction in Cost It reduces the need for traditional storm water infrastructure, which may reduce the overall.
5. Effective waste management Utilization of waste materials such flyash

##### Disadvantages

1. Traffic Loads and Volumes Observations differ on whether low or medium traffic volumes and weights are appropriate for porous pavements.
2. Lack of Standard Test Method This subject is a matter of research over the past time, and hence, it does not still have a standard method for testing.

**VI. MAINTENANCE**

1. The overall maintenance goal for a permeable paving system is to prevent clogging of the void spaces within the surface material.
2. The surface must not be sealed or repaved with nonporous materials if it is to continue to function and to be counted towards meeting the maximum allowed parking requirement
3. Sand and salt must not be applied to areas with porous pavements
4. Depending on the system, occasional sweeping or vacuuming of debris will be required to ensure the void spaces do not clog
5. Educational signage should be used wherever porous pavement is installed as a teaching tool for the public and as a reminder of maintenance obligations
6. In preparing the site prior to construction, drainage of surrounding landscaping should be designed to prevent flow of materials onto pavement surfaces
7. Soil, rock, leaves, and other debris may infiltrate the voids and hinder the flow of water, decreasing the utility of the pavement
8. Landscaping materials such as mulch, sand, and topsoil should not be loaded on pervious concrete, even temporarily.

**VII. CONCLUSION**

From the experimental results of investigation, the following conclusions can be made. Porous concrete allows water passes through it. It is not composed of fine aggregates. Aggregate having size more than 20mm cannot be used, because of larger voids cause settle down of cement slurry. And aggregates having size less than 10mm can give better results. Effective utilization of waste product (fly ash), and making it as a eco-friendly concrete. Lesser percentage of fly ash gives high strength than higher percentage. Higher percentage of fly ash weaker in cement bonding. Conplast Sp 500 is good admixture, and it increases the strength and bonding between cement and aggregates.

**VIII. RESULT**

% of Material	7 Days (Mpa)
0	20.32
5	23.73
10	25.20
15	19.02

**IX. ACKNOWLEDGMENT**

We are extremely thankful to our guide Prof. Prataprao Patil under whom our project took the shape of reality from mere idea. We are thankful to our guide for enlightening us with his/her precious guidance and constant encouragement. We thank our guide for providing us with ample support and valuable time. We are indebted to our guide who constantly provided a stimulus to reach our goals. We are grateful to Prof. Prashant L. Jadhav,

HOD of Civil department, Zeal polytechnic narhe pune, for his/her kind co-operation and timely help. We express our gratitude towards Prof. Udhav Shid, Director Academics & Admissions Zeal Education Society, narhe Pune., for his never ending support, planning and motivation.

We express our gratitude towards Prof. Ayub A. Tamboli, Principal Zeal polytechnic narhe pune, for his never ending support and motivation.

Lastly, we would like to thank all those who were directly or indirectly related to our project and extended their support to make the project successful.

If Live Project so/if necessary:-

Also, we would like to thanks industry resource person/other college Co-guide name who imparted us their valuable guidance timely.

**REFERENCES**

- [1] Darshan S. Shah, Prof. Jayeshkumar Pitroda, Prof. J.J. Bhavsar, ( August 2 013 ) "Pervious Concrete: New Era For Rural Road Pavement", International Journal of Engineering Trends and Technology (IJETT) – Volume 4 Issue 8
- [2] James, Bob. (2010) "Pervious Concrete–When it Rains, it Drains!" Directory of Marketing and Technical Standards.
- [3] Jeet Yadu, ( 2016 ), "Permeable Pavement & its Application-A Case Study", International Journal of Interdisciplinary Research (IJIR) Vol-2, Issue-7, ISSN: 2454 -1362
- [4] H. M. Imran, Shatirah Akib and Mohamed Rehan Karim , (2013) "Permeable Pavement and Stormwater Management System : A Review." In Environmental Technology
- [5] M. Admure , A. V. Gandhi , S. S. Adsul , A. A. Agarkar , G. S. Bhor and G . P. Kolte, ( Apr -2017) "Permeable

Pavements: New Technique For Constructi on Of Road Pavements in India",International Research Journal of Engineerin g and Technology (IRJET) Volume: 04 Issue: 04