Study on Light Weight Concrete-A Review

Ashutosh Chaudhary¹, Ajay Kumar Patel², Vijendra Kushwaha³, Vivek Singh⁴, Mr. Deepak Yadav⁵

^{1, 2, 3, 4} Dept of Civil Engineering

⁵Assistant Professor, Dept of Civil Engineering ^{1, 2, 3, 4, 5}bansal Institute Of Engineering And Technology

Abstract- Lightweight concrete, often referred to as foam concrete or aerated concrete, is a versatile construction material with a wide range of applications. It is formulated by incorporating a foaming agent into the concrete mixture, resulting in the formation of numerous air bubbles that reduce its density while maintaining structural integrity. The production of foam concrete involves the generation of as table foam using a foaming agent, which is then mixed with cement, sand, and other additives. The resulting mixture is a light weight, porous material with enhanced insulation properties, reduced weight, and improved workability.

Keywords- Water absorption test, Compressive strength test, Compare with Light Weight Concrete and Normal Concrete unit weight

I. INTRODUCTION

Lightweight concrete with foam, often referred to as foam concrete or aerated concrete, is a type of concrete that incorporates air bubbles or foam into its composition, resulting in a lighter and more insulating material compared to traditional concrete. It is commonly used in construction for its unique properties. Here's a brief introduction.[1]. Composition: Foam concrete is made by mixing a cementitious material (usually Portland cement or fly ash), water, and a stable foam. The foam is typically generated by mixing a foaming agent with water and air. [2].Lightweight Aggregate: The inclusion of air bubbles or foam in the mixture significantly reduces the density of the concrete. This makes foam concrete much lighter than conventional concrete, which is advantageous for various applications.[3].Insulation: Due to its lower density, foam concrete has excellent thermal insulation properties. It is often used in construction projects where insulation is a priority, such as in walls and roofs.[4].Fire Resistance: Foam concrete can have good fireresistant qualities, depending on the specific formulation. This makes it suitable for fireproofing applications.[5].Ease of Handling: Its lightweight nature makes foam concrete easier to handle and transport on construction sites compared to heavy traditional concrete.

II. LITERATURE REVIEW

Namsonea et al (2017) [1]. "Durability Properties of High Performance Foamed Concrete". The author of this paper discussed low density, excellent thermal characteristics, and moderate strength. Another type of cellular concrete is FC. Depending on the application, a variety of densities can be achieved by aerating cement mortar with foaming agents and controlling the ratios of cement, sand, water, and foaming agent. FC is created with cement mortar, a foaming agent, and no additional heat processing. It is crucial to take FC durability into consideration, particularly in cold and damp conditions. Mechanical environment strength, water absorption, and frost resistance are key factors in durability. shrinkage shrinkage Additionally, (including from carbonation) needs to be taken into account. Carbonation processes are sped up by a material's low density and high open porosity.

Mohd et al (2017) [2] "Applications of Foamed Light weight Concrete". The author said about Foamed concrete with densities between 400 kg/m3 and 1600 kg/m3 and an improvement in the workability and bond adhesion will also increase the flexural and tensile strength. the strengths of foamed concrete foamed concrete is developed is between the 100kg/m³ to 15000 kg/m3

Habsya et al (2018) [3] "Physical, mechanical and thermal properties of lightweight foamed concrete with fly ash". The purpose of this research is to determine how the fly ash content affects the density, thermal conductivity, compressive strength, and water absorption in lightweight foamed concrete (LFC) Cement, water, sand, fly ash (FA), and foam make up this LFC. A 1:1 water-to-cement ratio and a 1:4 cement-toaggregate ratio are used to create LFC.

Sand and FA made up the aggregates, which varied in weight by 0%, 10%, 20%, and 30%. Foam made up between 30 and 40 percent of the volume of the mortar.

Hameed et al (2021) [4]. "Experimental Study on Foam Concrete". In this study the author had studied the effect of mech- anical properties of foamed concrete by the replacement of cement with 0%,10% and 20% of fly ash and also by the addition of fibers at dosages of 1%, 1.5%. It was observed that the compressive strength of foamed concrete is about 5N/mm2 when cement is replaced with fly ash at 10% dosage and by the addition of fibers the split ten sile strength was increased when compared to conventional mix.

III. CONCLUSION

Light Weight Concrete is becoming very popular day by day. In this project the performance of Light Weight Concrete obtained from mixing fly ash and aerating agent(Kemilite-PR-Protein Based Foaming Agent) in conventional concrete will be analysed.Mechanical properties of foamed concrete depends on the foam volume, type and volume of fiber and the compressive strength is influenced by the shape, size and method of pore formation, age of the sample, direction of loading, characteristics of ingredients used and method of curing.

REFERENCES

- K.Krishna Bhavani Siram, "Cellular Light-Weight Concrete Blocks as a Replacement of Burnt Clay Bricks", International Journal of Engineering and Advanced Technology (IJEAT) ISSN: 2249 – 8958, Volume-2, Issue-2, December 2012.
- [2] Dhrumil s. chokshi , Ashish H. Makwana " Study on comparsion of fly ash bricks and clay bricks (ISSUE 5, DECEMBER 2013)
- [3] Carkner, P.M. "Lightweight insulating concrete and method for using same", U.S.Patent no.6290769.
- [4] M.R. Divya., Prof. M. Rajalingam, Dr.Sunilaa George (2016)"Study on Concrete with Replacement of Fine aggregates by Vermiculite", International Journal of New Technology and Research, Volume 2, Issue-5, pages 87-89
- [5] M.R. Divya., Prof. M. Rajalingam, Dr.Sunilaa George (2016)"Study on Concrete with Replacement of Fine aggregates by Vermiculite", International Journal of New Technology and Research, Volume 2, Issue-5, pages 87-89
- [6] Keun-Hyeok Yang, Kyung-Ho Lee (2015) Tests on highperformance aerated concrete with a lower density Construction and Building Materials 74 pp. 109–117
- [7] Mix design and properties of fly ash waste lightweight aggregates in structural lightweight concretel by Manu S. Nadesan, P. Dinakar School of Infrastructure, Indian Institute of Technology, Bhubaneswar, India.
- [8] A.Yeginobali, K. G. S. and M. T. (2003). High Strength Natural Lightweight Aggregate concrete with silica fume. Turkey.